



Semi-Traction Bloc Battery

NM06180T1TG

(6V 184Ah @ 5hr)

Nordmax valve regulated lead-acid batteries for the light traction market. With an innovative Gel-technology and maintenance free design, Nordmax Gel Bloc batteries are compatible with all universal cyclic applications.





Electrical Specifications

Voltage	6V		
80% DOD Voltage Cutoff	5.6V		
Self Discharge	Less than 3% per month (20°C/68°F)		
Charge Temperature	Min: -10°C (14°F) / Max: 50°C (122°F)		
Discharge Temperature**	Min: -40°C (-40°F) / Max: 50°C (122°F)		
Storage	Min: -20°C (-4°F) / Max: 60°C (140°F)		

Amp Hours (AH)						
			3 hr			
210	198	184	171	156	133	


**CAUTION: Depths of discharge, operating voltages and currents, when designing systems for use at maximum temperatures, will vary.

Mechanical Specifications

Industry Reference		-		
Length (A)	9.5 in 242 mm			
Width (B)	7.3 in	7.3 in 186 mm		
Height (C)	9.9 in	251 mm		
Height (D)	10.8 in	274 mm		
Weight	71 lbs	32 kgs		
Terminal (Opt'l)*	A-POLE			
Cell(s)	3			
Electrolyte	Gel			
Terminal Torque Nm	8			

NOTE: There is a tolerance of +/-2%. * Including A-Terminal





Features

Maintenance-free bloc batteries in Gel technology (no topping up during lifetime)

Good high current performance for extreme operating conditions

High-class patented safety valve

700 cycles (DIN EN 60254-1) (IEC 254-1)

Valve-regulated lead-acid battery

Recyclable

Long cycle life

Low self discharge rate allows for up to 2 years shelf life

Classified as a non-spillable battery is not restricted for transportation by:

- Air (IATA/ICAO provision 67)
- Ground (STB, DOT-CFR-HMR49)
- Water (IMDG amendment 27)

Applications

Electric vehicles

Wheelchairs

Cleaning machines

Electric working platforms

Universal for multiple cyclic applications

Compliant with

EN60254-1&2 & IEC254-1/2 ISO 7176-25 & SAE J 1495



Charging profile


IU Charging

 $I = min. 12\% C_5 max. 18\% C_5$ U = 2.4 V per cell

IUI Charging


I1 = min. 12% C_5 max. 18% C_5 U = 2.35 V per cell I2 = 1.5 % C_5 for max. 4 hours

Self discharge at different temperatures




20°C 30°C 40°C

Capacity vs. temperature




Relation between charging, voltage and temperature



OCV max

Storage: Determine the state of charge







10°C