



Light Traction Bloc Batteries

NM12063M6TG

(12V 71Ah @ 5hr)

Nordmax valve regulated lead-acid batteries for the light traction market. With an innovative Gel-technology and maintenance free design, Nordmax Gel Bloc batteries are compatible with all universal cyclic applications.





Electrical Specifications

Voltage	12V		
80% DOD Voltage Cutoff	11.2V		
Self Discharge	Less than 3% per month (20°C/68°F)		
Charge Temperature	Min: -10°C (14°F) / Max: 50°C (122°F)		
Discharge Temperature**	Min: -40°C (-40°F) / Max: 50°C (122°F)		
Storage	Min: -20°C (-4°F) / Max: 60°C (140°F)		

Amp Hours (AH)						
20 hr	10 hr	5 hr	3 hr	2 hr	1 hr	
78	74	71	64	61	60	


**CAUTION: Depths of discharge, operating voltages and currents, when designing systems for use at maximum temperatures, will vary.

Mechanical Specifications

Industry Reference	24		
Length (A)	10 in 254 mm		
Width (B)	6.6 in	168 mm	
Height (C)	8.0 in	202,5 mm	
Height (D)	8.1 in	204,5 mm	
Weight	55 lbs	25 kgs	
Terminal (Opt'l)*	M6		
Cell(s)	6		
Electrolyte	Gel		
Terminal Torque Nm	6		

NOTE: There is a tolerance of +/-2%. * Including A-Terminal





Features

Maintenance-free bloc batteries in Gel technology (no topping up during lifetime)

Good high current performance for extreme operating conditions

High-class patented safety valve

700 cycles (DIN EN 60254-1) (IEC 254-1)

Valve-regulated lead-acid battery

Recyclable

Long cycle life

Low self discharge rate allows for up to 2 years shelf life

Classified as a non-spillable battery is not restricted for transportation by:

- Air (IATA/ICAO provision 67)
- Ground (STB, DOT-CFR-HMR49)
- Water (IMDG amendment 27)

Applications

Electric vehicles

Wheelchairs

Cleaning machines

Electric working platforms

Universal for multiple cyclic applications

Compliant with

EN60254-1&2 & IEC254-1/2 ISO 7176-25 SAE J 1495



Charging profile


IU Charging

 $I = min. 12\% C_5 max. 18\% C_5$ U = 2.4 V per cell

IUI Charging


I1 = min. 12% C_5 max. 18% C_5 U = 2.35 V per cell I2 = 1.5 % C_5 for max. 4 hours

Self discharge at different temperatures




20°C 30°C 40°C

Capacity vs. temperature




Relation between charging, voltage and temperature



OCV max

Storage: Determine the state of charge







10°C